

DERMABIT 4170



High performance torch-on waterproofing membrane for multi-layer application, with or without insulation.

Product Pluses: Guaranteed by more than 25 years in the field, versatile and reliable at any latitude, extensive thermal operating range (-15°C/+150°C), fast and easy to apply, excellent resistance to ageing.

APP Elasto-Plastomeric Membranes

Lab Tests	Test Performed	Unit of Measurement	Result
Thickness	UNI EN 1849-1	mm	4
Mass per unit area	UNI EN 1849-1	Kg/m ²	4
Ultimate tensile strength Longitudinal resistance at break Transverse resistance at break	UNI EN 12311-1	N N	950 650
Elongation at break Longitudinal elongation at break Transverse elongation at break	UNI EN 12311-1	% %	50 50
Flexibility at Low Temperature	UNI EN 1109	° C	-15
Dimensional Stability to Heat	UNI EN 1107-1	%	±0.3
Creeping at Heat	UNI 8202/18	° C	+130