

## Fix ALL Flexi

Revision: 3/02/2018

Page 1 from 3

### Technical data

Basis	SMX Hybrid Polymer
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (20°C / 65% R.H.)	Ca. 10 min
Curing speed * (20°C / 65% R.H.)	2 mm/24h → 3 mm/24h
Hardness	40 ± 5 Shore A
Density	1,67 g/ml
Elastic recovery (ISO 7389)	> 75 %
Maximum allowed distortion	± 20 %
Max. tension (DIN 53504)	1,80 N/mm <sup>2</sup>
Elasticity modulus 100% (DIN 53504)	0,75 N/mm <sup>2</sup>
Elongation at break (DIN 53504)	750 %
Temperature resistance	-40 °C → 90 °C
Application temperature	5 °C → 35 °C

(\*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

### Product description

Fix ALL Flexi is a high quality, neutral, elastic, 1-component construction joint and adhesive sealant based on SMX Hybrid Polymer.

### Properties

- Good extrudability
- Stays elastic after curing and very sustainable
- Excellent adhesion on nearly all surfaces, even if slightly moist.
- Can be painted with water based systems
- No odour.
- Very low emission, EC1 PLUS R certified
- Impervious to mould, contains ZnP (biocide with fungicidal action)
- Does not contain solvents, isocyanates, acids, halogens and toxic components, completely neutral.
- Colourfast.
- Good weather and UV resistance

### Applications

- Sealing and bonding in the building and construction industry.
- Strong elastic bonding in vibrating constructions.
- Sanitary applications.

- Sealing of floor joints.
- Sealing and bonding in the building and construction industry.

### Packaging

*Colour:* white, black, grey, brown, beige  
*Packaging:* 290 ml cartridge

### Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

### Chemical resistance

Good resistance to (salt)water, aliphatic solvents, hydrocarbons, ketones, esters, alcohols, diluted mineral acids and alkalis. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

---

## Fix ALL Flexi

---

Revision: 3/02/2018

Page 2 from 3

### Substrates

*Substrates:*

*Nature:* clean, dry, free of dust and grease.

*Surface preparation:* Porous surfaces in water loaded applications should be primed with Primer 150. All smooth surfaces can be treated with Soudal Surface Activator. The surfaces should be degreased before bonding them together.

Fix ALL Flexi has been tested on the following metal surfaces: steel, AlMgSi1, brass, electrolytic galvanised steel, AlCuMg1, flame galvanised steel, AlMg3 and steel ST1403. We recommend a preliminary adhesion test on every surface. Fix ALL Flexi has an excellent adhesion on most common substrates: . Fix ALL Flexi also has a good adhesion on plastics: polystyrene, polycarbonate (Makrolon®), PVC, ABS, polyamide, PMMA, fiberglass reinforced epoxy, polyester. While producing plastics very often releasing agents, processing aids and other protective agents (like protection foil) are used. These should be removed prior to bonding. For optimum adhesion the use of Surface Activator is recommended. NOTICE: bonding plastics like PMMA (e.g. Plexi® glass), polycarbonate (e.g. Makrolon® or Lexan®) in stress loaded applications can give rise to stress cracking and crazing in these substrates. The use of Fix ALL Flexi is not recommended in these applications. There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary adhesion test on any substrate.

### Joint dimensions

*Min. width for bonding:* 2 mm

*Min. width for joints:* 5 mm

*Max. width for bonding:* 10 mm

*Max. width for joints:* 30 mm

*Min. depth for joints:* 5 mm

Recommendation sealing jobs: joint width = 2 x joint depth.

### Application method

*Application method:* With manual- or pneumatic caulking gun.

*Cleaning:* With Fix ALL Cleaner immediately after use.

*Finishing:* With a soapy solution or Soudal Finishing Solution before skinning.

*Repair:* With the same material

### Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label for more information.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

---

## Fix ALL Flexi

---

Revision: 3/02/2018

Page 3 from 3

**Remarks**

- Fix ALL Flexi may be overpainted with water based paints, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application.
- The drying time of alkyd resin based paints may increase.
- Fix ALL Flexi can be applied to a wide variety of substrates. Due to the fact that specific substrates such as plastics, like polycarbonate, etc, may differ from manufacturer to manufacturer, we recommend preliminary compatibility test.
- Fix ALL Flexi can not be used as a glazing sealant.
- Not suitable for bonding aquariums.
- Fix ALL Flexi can be used for adhering of and sealing on natural stone.
- When applying, make sure not to spill any sealant on the surface of materials.
- The sanitary formula should not replace regular cleaning of the joint. Excessive contamination, deposits or soap remainings will stimulate the development of fungi.
- A total absence of UV can cause a color change of the sealant.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.

**Standards and certificates**

- Tested according to ISO 16938-1 (Testing for staining on natural stone by sealants).

**Environmental clauses***Lead regulation:*

Fix ALL Flexi conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED® 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

**Liability**

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.