



Certificate of performance

product:	Gerband 186
description:	polyacrylate adhesive on special paper very high tack, outstanding ageing resistance
application:	air-tight bonding and sealing of penetrations and overlaps of wind and vapour barriers according to DIN 4108-7
surface treatment:	The surface shall be clean, dry and free of grease, oil and surfactants.

property	unit	value	testing method
total thickness	mm	0,42	DIN EN 1942
tensile strength	N/ 25 mm	> 250	DIN EN 14410
Elongation	%	3-5	DIN EN 14410
adhesion	N/ 25mm	> 40	DIN EN 1939
processing temperature	°C	+5 to +40	-
storage temperature	°C	+5 to +25	-
Temperature range	°C	-40°C to + 80°C	-

Nördlingen, 10.04.2014

Dr. Dirk Ferber
Responsible for final inspection